

# Mixed Media

GLAZED PORCELAIN

BEST TILE® / BESTTILE.COM

# Aglow


## COLORS, SIZES & AVAILABILITY

NOMINAL SIZE	FINISH	THICKNESS	GROUT JOINT	BIANCO	GRIGIO	NERO	TAUPE
4 x 12	Glossy	10 mm	1/8"	✓	✓	✓	✓
12 x 24	Matte	10 mm	1/8"	✓	✓	✓	✓
2 x 2 Mosaic	Matte	10 mm	N/A	✓	✓	✓	✓
.8 x 12 Quarter Round	Glossy	10 mm	1/8"	✓	✓	✓	✓

✓ Stock Item. ⌚ Non-Stock Item. Requires Extra Lead Time.

## TECH INFO

R = Residential, LC = Light Commercial, C = Commercial

<p><b>ORIGIN:</b> Italy</p> <p><b>SHADE VARIATION:</b> V3 - Moderate Variation</p> <p><b>WEAR RATING:</b> Taupe Matte / Bianco: Class 4 - Rated for all residential and light commercial applications; Taupe Glossy / Grigio / Nero: Class 3 - Rated for all residential applications.</p> <p>It is not recommended to stagger any tile longer than 15" more than 1/3 the length of the tile.</p> <p> Contains 16% Pre-Consumer Recycled Content.</p>	RECOMMENDED APPLICATIONS	R	LC	C
	FLOORS	●	✦	
	WALLS / BACKSPLASH	●	●	●
	POOL DECKING			
	EXTERNAL USE - FROST PROOF	*		

● Approved for this application. ✦ Taupe Matte & Bianco approved for this application. \* Discuss proper installation method with your Sales Representative.

## TILE PERFORMANCE DATA

TECHNICAL FEATURE	NORMS	RESULTS
Water Absorption	ISO 10545-3	≤ 0.5 %
Abrasion Resistance (Glazed)	ISO 10545-7	3 / 4
Breaking Strength	ISO 10545-4	≥ 35 N/mm2
Dynamic Coefficient of Friction Wet	AcuTest	≥ 0.42 (Matte)
Dimensions Range	ISO 10545-2	Conforms
Frost Resistance	ISO 10545-12	Frost Proof
Chemical Resistance - Household Chemicals	ISO 10545-13	A/LA/HA
Chemical Resistance - Low Concentration of Acids and Bases	ISO 10545-13	A/LA/HA
Resistance to Stains	ISO 10545-14	Min Class 3
Crazing Resistance of Glazed Tiles	ISO 10545-11	Resistant

Always inspect materials prior to installation. Always mix 2-3 cartons at a time while installing to ensure the best blend. All product images are representative only. Variation in color and shading is to be expected. Final selection should be made from actual tile samples.